


CHEMICAL NAME

1,3-Diphenyl-1,1,3,3-tetrakis(dimethylsiloxy)-disiloxane

CHEMICAL STRUCTURE



INTRODUCTION

SiSiB[®] PF8802 is a colorless clear liquid.

TYPICAL PHYSICAL PROPERTIES

| | |
|--------------------------|--|
| CAS No. | 66817-59-2 |
| EINECS No. | N.A. |
| Formula | C ₂₀ H ₃₈ O ₅ Si ₆ |
| Molecular Weight | 527.03 |
| Flash Point: | >110°C |
| Boiling Point: | 96°C [0.25mmHg] |
| Color and Appearance | Colorless clear liquid |
| Specific Gravity at 25°C | 1.005 |
| Refractive Index | 1.4622 |
| Purity: | Min.95.0% |

Power Chemical
ISO9001 ISO14001 certificated

Copyright© 2008 Power Chemical Corporation Ltd.
SiSiB[®] is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia



SiSiB[®] PF8802 SILOXANE

- 2 -

APPLICATIONS

SiSiB[®] PF8802 can be used as crosslinkers for liquid silicone rubber, phenyl silicone rubber and phenyl resin.

PACKING AND STORAGE

SiSiB[®] PF8802 is supplied in 1Kg bottles, 5Kg 25Kg pails, and 200Kg steel drums.

In the original unopened packaging, SiSiB[®] PF8802 has a shelf life of 60 months.

NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: support@SiSiB.com.

Power Chemical
ISO9001 ISO14001 certificated

Copyright© 2008 Power Chemical Corporation Ltd.
SiSiB[®] is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia